

AP 03

Test report C/23491/T01a Test 11 Spec 272
Nocturne MDF panel, 6mm perforations at 16mm centres,
50mm Rockwool backing
Sound absorption coefficient BS EN ISO 354: 0.60
BS EN ISO 11654: Class C

